

THIN FILM CAPACITOR, ITS MANUFACTURE AND WORKING METHOD OF ELECTRODE

Patent number: JP10163447
Publication date: 1998-06-19
Inventor: KATOU YOSHITAKE; SONE SHUJI; ARITA KOJI
Applicant: NIPPON ELECTRIC CO
Classification:
- international: *H01L21/3065; H01L21/461; H01L21/822; H01L21/8242; H01L27/04; H01L27/108; H01L21/02; H01L21/70; H01L27/04; H01L27/108; (IPC1-7): H01L27/108; H01L21/3065; H01L21/461; H01L21/822; H01L21/8242; H01L27/04*
- european:
Application number: JP19960321636 19961202
Priority number(s): JP19960321636 19961202

Report a data error here

Abstract of JP10163447

PROBLEM TO BE SOLVED: To realize a thin film capacitor wherein leak current density is small, by forming a first electrode layer which is in contact with at least a high permittivity film of an upper electrode film and has a specified thickness, of ruthenium or ruthenium oxide. **SOLUTION:** In a thin film capacitor, BST is used as a high permittivity film 2, and a silicon (Si) substrate 5 has a surface which is SiO₂ 4 formed by heat treatment, on which substrate 5 the following are formed; Pt as a lower electrode 3, a high permittivity film 2, and single layer Ru as upper electrodes which are 30nm in thickness. An upper electrode film 1 is composed a single layer or a plurality of layers. The first electrode layer which is in contact with at least the high permittivity film 2 is composed of ruthenium(Ru) or ruthenium oxide (RUO₂). It is especially important that the thickness of the layer is less than 50nm and greater than or equal to 5nm. Thereby a thin film capacitor excellent in electric characteristics can be realized.

Data supplied from the **esp@cenet** database - Worldwide